## AMENDMENTS TO THE CLAIMS

Listing Of Claims:

1.   (Currently Amended) A method of servicing a wellbore in contact with a subterranean formation, comprising: displacing a sealant composition comprising a colloidally stabilized latex into the wellbore, wherein the sealant composition does not comprise ~~an epoxy resin or~~ zinc oxide, <u>wherein the colloidally stabilized latex comprises a polymer, and wherein the polymer comprises an ethylenically unsaturated surfactant, a functionalized silane, or combinations thereof</u>.

2.   (Original) The method of claim 1, wherein the colloidally stabilized latex comprises:

    (a)   an aliphatic conjugated diene monomer;

    (b)   an additional monomer comprising a non-aromatic unsaturated mono- or di-carboxylic ester monomer, an aromatic unsaturated monomer, a nitrogen-containing monomer, or combinations thereof; and

    (c)   a protective colloid.

3.   (Original)   The method of claim 2, wherein the protective colloid comprises polyvinylalcohol, a cellulose ether, a natural gum, a synthetic gum, polyacrylic acid, an acrylate, a poly(vinyl alcohol)co(vinyl amine) copolymer, or combinations thereof.

4.   (Canceled)

5.   (Currently Amended) The method of ~~claim 2~~ <u>claim 1</u>, wherein the colloidally stabilized latex comprises an oxyalkylene functional monomer comprising

$$a \quad H_2C=C(R)C\overset{O}{\overset{\|}{C}}-O-(CH_2-CH-O)_n-R'',\; \overset{R'}{|}$$

$$a \quad OH-\overset{O}{\overset{\|}{C}}-CH=CH-\overset{O}{\overset{\|}{C}}-O-(CH_2-CH-O)_n-R',\; \overset{R}{|}$$

a monoester of mono- or di- carboxylic acid, a diester of dicarboxylic acid, or combinations thereof, wherein R is hydrogen or a C_1-C_4 alkyl, R' is hydrogen or a C_1-C_4 alkyl, R" is hydrogen or a C_1-C_4 alkyl, and n is in a range of from 1 to 30, and wherein the oxyalkylene functional monomer copolymerizes with the aliphatic conjugated diene monomer and the additional monomer.

6. (Currently Amended) The method of ~~claim 2~~ claim 1, wherein the ~~colloidally stabilized latex comprises a~~ functionalized silane [[is]] generally represented by:

$$(R'')_{3-m}$$

$$|$$

$$R(CH_2)_n Si(OR')_m,$$

wherein R" is a C_1 to C_5 alkyl, R' is a C_1 to C_5 alkyl, R is SH, $CH_2=CH-$, $CH_2=C(CH_3)-C(O)O-$, $CH_2=CH-C(O)O-$, or

,

n is in a range of from 1 to 10, and m is 2 or 3.

7. (Canceled)

8. (Currently Amended) The method of ~~claim 2~~ claim 36, wherein the salt comprises a monovalent ion, a divalent ion, or combinations thereof.

9. (Original) The method of claim 1, wherein the sealant composition comprises salt.

10. (Original) The method of claim 1, wherein the sealant composition comprises fibers, beads, or combinations thereof.

3

11.   (Original) The method of claim 1, wherein the sealant composition comprises a cement slurry.

12.   (Original) The method of claim 8, wherein the sealant composition is displaced into an annulus of the wellbore and allowed to set.

13.   (Original) The method of claim 1, wherein the sealant composition is positioned in the wellbore to isolate the subterranean formation from a portion of the wellbore, to support a conduit in the wellbore, to plug a void or crack in the conduit, to plug a void or crack in a cement sheath disposed in an annulus of the wellbore, to plug an opening between the cement sheath and the conduit, or combinations thereof.

14.   (Original) The method of claim 1, wherein the colloidally stabilized latex comprises a vulcanizable group, a vulcanizing agent, a vulcanization accelerator, a vulcanization retarder, or combinations thereof.

15.   (Original) The method of claim 1, wherein the colloidally stabilized latex comprises a crosslinkable monomer, an acidic catalyst, a thermosetting resin, or combinations thereof.

16.   (Original) The method of claim 1, further comprising combining a drilling fluid with the sealant composition near a loss-circulation zone, thereby forming a solid mass in the loss-circulation zone.

17 – 35 (Canceled).

36.   (Previously Presented)   The method of claim 1, wherein the collodially stabilized latex remains substantially stable in the presence of salt.